PHPA – HIGH TEMPERATURE

SHALE STABLISERS

INSH 4000 - PRODUCT DATA SHEET



Description

PHPA – a shale inhibitor and rheology modifier – is a high molecular weight anionic polyacrylamide, designed primarily to provide shale stability and viscosity in water-based drilling fluids. Dry PHPA powder disperses rapidly without balling or fish eyes. The product maintains borehole stability by preventing shale swelling and erosion. High temperature PHPA is stable up to 140°C.

Application

PHPA can be used as a shale inhibitor and rheology modifier in freshwater, seawater and sodium or potassium chloride brines, and is very effective in sweeps to aid in hole cleaning.

Specifications

Advantages

- Functions as an inhibitor by coating or encapsulating formation & cuttings
- Restricts the interaction of water hydratable & dispersible shale
- · Can be used as a flocculent in clear water drilling
- High viscosity helps in better removal of cuttings from bore hole
- Resistant to bacterial degradation

| S.No. | Parameter | Specification |
|-------|-------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------|
| 1 | Physical State | Free flowing powder, free from lumps and visible impurities |
| 2 | Moisture content at 105±2°C, percent by mass | 7 (Maximum) |
| 3 | Ionic Character | Anionic |
| 4 | Relative Dispersibility of Bentonite pellets in 0.2% (w/v) polymer solution at $60\pm5^{\circ}$ C with respect to distilled water | 175 (Maximum) |
| 5 | Degree of Hydrolysis, as determined by electrometric titration, percent by mass | 20.0 to 40.0 |
| 6 | Apparent Viscosity of 0.2% (w/v) polymer solution in distilled water at $24\pm2^{\circ}$ C, cP | 9 (Minimum) |
| 7 | Apparent Viscosity (at $24\pm 2^{\circ}$ C) of 0.2% (w/v) polymer solution after ageing at 110 $\pm 2^{\circ}$ C for 18 hrs. | Not less than 80% of the value obtained without ageing |
| 8 | Apparent Viscosity of 4 cP Bentonite suspension with 0.2% (w/v) polymer concentration at 24±2°C and pH 9.0, cP | 15 (Minimum) |
| 9 | Apparent Viscosity (at 24±2°C) of 4 cP Bentonite Suspension with 0.2% (w/v) polymer concentration after ageing at 140±2°C for 24 hrs., cP | Not less than 80% of the value obtained without ageing |
| 10 | Apparent Viscosity of 0.4% (w/v) polymer solution in distilled water in presence of 100 ppm Ca++ at 24±2°C, cP | Not less than 60% of the value obtained without Ca++ treatment |

Packaging

25 Kgs pre ply kraft paper bag. Customized packaging is available on request.

© Indusun Fluids 2020

This product data sheet is produced only for informational purposes and under no circumstances can be treated as a guarantee or warrantee furnished by Indusun Fluids.